

Test	Standard	Result	Measured unit
Density	ISO 845	70	Kg/m ³
Tensile strength - MD	ISO 1798	692	kPa
Tensile strength - TD	ISO 1798	575	kPa
Elongation - MD	ISO 1798	141	%
Elongation - TD	ISO 1798	148	%
Compression 10%	ISO 844	80	kPa
Compression 25%	ISO 844	105	kPa
Compression 50%	ISO 844	191	kPa
Compression Set-0.5 Hrs	ISO 1856	6	%
Compression Set-24 Hrs	ISO 1856	3	%
Compression Set 50% 0.5 Hrs	ISO 1856	17.5	%
Compression Set 50% 24 Hrs	ISO 1856	10	%
Working Temperature Range	Internal	-60 \ 90	°C
Water Absorption %Vol (max)	Internal	1	%
Thermal Conductivity at 10C	ASTM C177	0.0430	W/mK
Thermal Conductivity at 40C	ASTM C177	0.0470	W/mK
Shore-OO	ASTM D2240	72	oo
Shore A	ASTM D2240	29	A

Galfoam is closed cell cross-linked polyethylene foam sheet, produced in an extrusion process. This information is presented to the best of our knowledge; Simply Foam Products Ltd reserve the right to modify it.

- WRAS approved for cold water use.
- Dimensional stability 24 hr at 70C < 2%.
- If pinholes were created during the foaming process, no more than 6 holes of diameter 2mm per 1m2 of sheet are acceptable.
- MD - machine direction - along the extruder's axis.
- TD - transverse direction - Perpendicular to the extruder's axis.
- Data represents typical values measured on a 10 mm thick specimen and should be considered as a guideline only.

For prices and online orders please visit www.foam.co.uk