

Test	Standard	Result	Measured unit
Density	ISO 845	45	Kg/m ³
Tensile strength	ISO 1798	446	kPa
Elongation	ISO 1798	227	%
Compression 10%	ISO 844	83	kPa
Compression 25%	ISO 844	100	kPa
Compression 50%	ISO 844	168	kPa
Compression Set 25% 0.5H	ISO 1856	7	%
Compression Set 25% 24H	ISO 1856	2	%
Compression Set 50% 0.5H	ISO 1856	21	%
Compression Set 50% 24H	ISO 1856	9.5	%
Working Temperature Range	Internal	-60 \ 90	°C
Water Absorption %Vol (max)	Internal	1	%
Thermal Conductivity at 10C	ASTM C177	0.044	W/mK
Thermal Conductivity at 40C	ASTM C177	0.046	W/mK
Shore	ISO 868	61	oo
Flammability	FMVSS302	43	mm/min

EFP45 is a closed cell cross-linked polyethylene foam sheet. This information is presented to the best of our knowledge; Simply Foam Products Ltd reserve the right to modify it.

- Dimensional stability 24 hr at 70C < 2%.
- Dimensional stability 24 hr at 90C < 5%.
- If airholes were created during the foaming process, no more than 5 holes of diameter 2mm per 1m2 sheet are acceptable.
- Data represents typical values measured on a 10 mm thick specimen and should be considered as a guideline only.

For prices and online orders please visit www.foam.co.uk